



This work has been carried out within the framework of the EUROfusion Consortium, funded by the European Union via the Euratom Research and Training Programme (Grant Agreement No 101052200 — EUROfusion). Views and opinions expressed are however those of the author(s) only and do not necessarily reflect those of the European Union or the European Commission. Neither the European Union nor the European Commission can be held responsible for them.

# Status of complete neutron-induced displacement damage cross section data

A.Yu. Konobeyev, D. Leichtle



# Content

- Introduction
- Methodology, Codes, Data, Assumptions
- Summary and Data

# Introduction

- Nuclear analysis support for design and safety of nuclear and accelerator facilities demand accurate and validated nuclear data.
- Specific interest in fusion technology applications, i.e. DT 14-MeV neutrons and d-Li neutron sources (IFMIF-DONES)
- Radiation damage due to irradiation with neutrons poses limitations on material performances and systems' lifetimes.
- European effort on provision of recommended nuclear data libraries, in particular nuclear response files – displacement damage.
- Libraries should cover a wide range of elements and energies.
  - Joint Evaluated Fission and Fusion (JEFF) nuclear data library.  
[JEFF Nuclear Data Library - NEA \(oecd-nea.org\)](http://oecd-nea.org)

# Methodology, Codes, Data, Assumptions

- Damage models and parameters
- Production of displacement cross sections
- Uncertainty propagation
- Processing to nuclear data libraries

# Damage Models and Parameters


## NRT

M.J. Norgett et al. (1975)

$$N_{NRT}(T) = \frac{0.8}{2E_d} \frac{T}{1 + k_L g(T/E_L)}$$

$$g(\varepsilon) = \alpha_1 \varepsilon^{1/6} + \alpha_2 \varepsilon^{3/4} + \alpha_3, \quad \alpha_4 = E_d$$

$$\alpha_1 = 3.4008, \alpha_2 = 0.40244, \alpha_3 = 1.0$$




S.P. Simakov et al. (2018)

## athermal recombination corrected dpa (arc-dpa)

K. Nordlund et al. (2015)

$$N_{arc-dpa}(T) = \left( \frac{1 - c_{arc}}{(2E_d/0.8)^{b_{arc}}} T^{b_{arc}} + c_{arc} \right) N_{NRT}(T)$$


$$\alpha_5 = b_{arc}, \alpha_6 = c_{arc}$$




# Damage Models and Parameters

- arc-dpa parameters
  - From experimental data and systematics

$$b_{\text{arcdfa}} = -0.82$$




- BCA-(MD/NRT/arcdfa) simulations
  - SRIM/IOTA codes
  - Combination of BCA simulations and MD/NRT/arcdfa Frenkel pair defect numbers



# Production of Displacement Cross Sections

- Data processing via NJOY2016, and other tools (e.g. PREPRO 2021)
- 78 Elements (Be...Bi) from JEFF-4T2.2 (also: JENDL-5, TENDL-2021, ENDF/B-VIII.0)
- Unphysical jumps in a series of cross-sections (Mg, Al, Si, P, S, Ar, K, Ca, Sc, Ti, Cr, Ni, Zn, Ga, Ge, As, Se, Pd, Sm, Tb, Er, Tm, Yb)
- Extension to 200 MeV, where necessary



# Production of Displacement Cross Sections

## ■ Extension to 200 MeV, where necessary


JEFF-4T1    all data: 22 %,     $3 \leq Z \leq 83$ : 13.5 %

TENDL-21    all data: 0.8 %,     $3 \leq Z \leq 83$ : 0.5 %

JENDL-5    all data: 27 %,     $3 \leq Z \leq 83$ : 20 %

ENDF/B-VIII    all data: 92 %,     $3 \leq Z \leq 83$ : 91 %

## ■ Bridging and smoothing



# Uncertainty Propagation

- MC Method (D.L. Smith, 2004)
  - Choice of basic set of model parameters
  - Estimation of standard deviations
  - MC sampling of input data sets
  - Calculation of output data sets
  - Statistical evaluation

$$p_k = \{p_{01} \pm \Delta p_{k1}, \dots, p_{0L} \pm \Delta p_{kL}\}$$

$$V_{i,j} = (1/K) \sum_{k=1,K}^K (\sigma_{ki} - \sigma_{0i})(\sigma_{kj} - \sigma_{0j})$$

$$\Delta\sigma_{d,ii} = \sqrt{V_{ii}}$$

# Uncertainty Propagation, Assumptions

## ■ Atomic displacement models


$$\Delta E_d / E_d = 20\%$$

NRT:  $\Delta \alpha_1 / \alpha_1 = \Delta \alpha_2 / \alpha_2 = \Delta \alpha_3 / \alpha_3 = 15\%$

Arc-dpa:  $\Delta b_{arc} / b_{arc} = \Delta c_{arc} / c_{arc} = 20\%$


## ■ Nuclear data uncertainties

- Covariance matrices from current JEFF/TENDL  
(light targets: previous TENDL)
- Random sampling from cross section covariances








# Uncertainty Propagation, Sampling

- Covariance matrices for displacement cross-sections from parameter uncertainties
  - Atomic displacement models
  - Covariance matrices from current JEFF/TENDL (light targets: previous TENDL)






# Uncertainties and Correlations



\*only nuclear data uncertainty

# Summary and data

## ■ NRT and arc-dpa displacement cross sections with covariance matrices



- Be...Bi (76 Elements)
- ENDF-6, ACE format
- MT 900: arcdpa, MT 901: NRT
- JEFF-4T2.2: <https://t1p.de/8toxr>
- Other nuclear data: <https://bit.ly/3L8ZIHQ>